

PRODUCT
IMPACT 66-H

LOW REBOUND, HOT GUNNING MIX
MEDIUM AGGREGATE

REFRACTORIES

TECHNICAL DATA

PHYSICAL PROPERTIES

Maximum Service Temperature	2900°F
ASTM C-401	Class D
Lbs. Required Dry Mix Per Cu. Ft.	130 lbs.
% Water by Weight Required for Gunning	Approx. 6 - 8%
Bulk Density After Drying at 230°F	133 lbs./cu.ft.
Cold Crushing Strength After Drying at 230°F	500 - 700 psi
MOR After Drying at 230°F	150 - 225 psi
MOR After Heating to 2750°F	750 - 1100 psi
<u>Permanent Linear Change</u>	
After Drying at 230°F	Negligible
After Heating to 1500°F	0.0 to -0.2%
After Heating to 2750°F	-0.4 to -0.6%

CHEMICAL ANALYSIS

Silica	[SiO ₂]	50.1%
Alumina	[Al ₂ O ₃]	45.2%
Iron Oxide	[Fe ₂ O ₃]	0.9%
Lime	[CaO]	1.7%

THERMAL CONDUCTIVITY BTU/SQ.FT./HR./°F/IN.

At 500°F	7.2
At 1500°F	7.3
At 2500°F	8.2

NOTE: All data subject to reasonable deviation and should not be used for specification purposes.

8810



MT. SAVAGE
SPECIALTY REFRACTORIES COMPANY • Pittsburgh, Pa. 15127 •