

PRODUCT

SUPER HEATCRETE 28

**LOW IRON, SUPER DUTY FIRECLAY CASTABLE
MEDIUM AGGREGATE**

REFRACTORIES

TECHNICAL DATA

PHYSICAL PROPERTIES

Maximum Service Temperature	2800°F
ASTM C-401	Class D
Lbs. Required Dry Mix Per Cu. Ft.	135 lbs.
% Water by Weight Required for Casting	Approx. 15%
Bulk Density After Drying at 230°F	140 lbs./cu.ft.
Cold Crushing Strength After Drying at 230°F	3600 - 4800 psi
MOR After Drying at 230°F	700 - 1050 psi

Permanent Linear Change

After Drying at 230°F	Negligible
After Heating to 1500°F	0.0 to -0.2%
After Heating to 2700°F	0.0 to 1.4%

CHEMICAL ANALYSIS

Silica	[SiO ₂]	42.5%
Alumina	[Al ₂ O ₃]	50.6%
Iron Oxide	[Fe ₂ O ₃]	0.9%
Lime	[CaO]	5.0%

THERMAL CONDUCTIVITY BTU/SQ.FT./HR./°F/IN.

At 500°F	5.8
At 1500°F	6.2
At 2500°F	6.6

NOTE: All data subject to reasonable deviation and should not be used for specification purposes.

2940



MT. SAVAGE

SPECIALTY REFRACTORIES COMPANY • Pittsburgh, Pa. 15127 •