

PRODUCT

**BLACK JACK 50 GUN MIX**

LOWER CEMENT SILICON CARBIDE CASTABLE

**REFRACTORIES**

**TECHNICAL DATA**

PHYSICAL PROPERTIES

Maximum Service Temperature	2800°F
ASTM C-401	Class D
Lbs. Required Dry Mix Per Cu. Ft.	155 lbs.
% Water by Weight Required for Gunning	Approx. 8%
Bulk Density After Drying at 230°F	160 lbs./cu.ft.
MOR After Drying at 230°F	700 - 1000 psi
MOR After Firing at 1500°F	700 - 1000 psi
MOR at 2400°F	500 - 800 psi

Permanent Linear Change

After Drying at 230°F	Negligible
After Heating to 1500°F	+/- 0.2%
After Heating to 2550°F	0.0 to -0.4%

CHEMICAL ANALYSIS

Silicon Carbide [SiC]	49.7%
Silica [SiO <sub>2</sub> ]	23.5%
Alumina [Al <sub>2</sub> O <sub>3</sub> ]	23.4%
Iron Oxide [Fe <sub>2</sub> O <sub>3</sub> ]	0.4%
Lime [CaO]	2.8%
Other (alkalies)	0.2%

NOTE: All data subject to reasonable deviation and should not be used for specification purposes.

5001



**MT. SAVAGE**

**SPECIALTY REFRACTORIES COMPANY** • Pittsburgh, Pa. 15127 •