

PRODUCT

ULTRA-TEK 65 UL VC
ULTRA-LOW CEMENT CASTABLE
VIBRATION CASTING

REFRACTORIES

TECHNICAL DATA

PHYSICAL DATA

Maximum Service Temperature	3100 °F
Water by Weight Required for Casting	5.0%
Bulk Density After Drying at 250°F	158 pcf
Modulus of Rupture After Drying at 250°F	2,000 – 2,800 psi
After Heating to 1500°F	4,000 – 6,000 psi
At 2550°F	1,400 – 2,000 psi
Cold Crushing Strength After Drying at 250°F	10,000 – 16,000 psi
After Heating to 1500°F	12,000 – 20,000 psi
C-704 Abrasion Resistance After Heating to 1500°F	3.8 cc
Permanent Linear Change After Heating to 1500°F	0.0 to -0.2%
After Heating to 2550°F	+0.5 to +1.4 %

CHEMICAL ANALYSIS

Silica	[SiO ₂]	30.6%
Alumina	[Al ₂ O ₃]	65.0%
Iron Oxide	[Fe ₂ O ₃]	0.9%
Lime	[CaO]	0.9%
Titania	[TiO ₂]	1.8%

NOTE: All data are based on averages and subject to reasonable deviation and should not be used for specification purposes.

0911



MT. SAVAGE
SPECIALTY REFRACTORIES COMPANY • Pittsburgh, Pa. 15127 •